

Damping mechanism for the strongly renormalized c -axis charge transport in high- T_c cuprate superconductors

Jae H. Kim, H. S. Somal, and D. van der Marel
*Laboratory of Solid State Physics, University of Groningen,
Nijenborgh 4, 9747 AG Groningen, The Netherlands*

A. M. Gerrits, and A. Wittlin
*High Field Magnet Laboratory, University of Nijmegen,
Toernooiveld 1, 6525 ED Nijmegen, The Netherlands*

V. H. M. Duijn, N. T. Hien, and A. A. Menovsky
*Van der Waals-Zeeman Laboratory, University of Amsterdam,
Valckenierstraat 65, 1018 XE Amsterdam, The Netherlands*
(Received)

We analyze the c -axis infrared reflectivity of $\text{La}_{1.85}\text{Sr}_{0.15}\text{CuO}_4$ single crystals. The plasma edge near 6 meV, observed below T_c , is due to Cooper-pair tunneling. This low value of the plasma edge is consistent with the c -axis plasma frequency (ν_p) obtained from LDA calculations (> 0.1 eV) if we take into account that the single-particle charge transport along the c axis is strongly incoherent both above and below T_c . We find no evidence for a reduction of the c -axis scattering rate (γ) below T_c . Our investigation suggests $\hbar\gamma > \hbar\nu_p \gg 3.5k_B T_c$, which is exactly opposite to the clean limit.

PACS numbers: 74.25.Gz, 78.30.Er, 71.45.Gm, 74.25.Nf

Materials Science Center Internal Report Number VSGD.94.6.1

One of the peculiar aspects of the high- T_c cuprate superconductors is the large anisotropy related to their layered structure. Although the anisotropy following from a conventional Fermi-liquid approach based on LDA (local density approximation) band structure calculations, is of the order 10 in most of these compounds, experimentally it is found to be much larger, as follows from *e.g.* the London penetration depth and the normal-state resistivity. In the clean limit the London penetration depth λ_L is given by $c^2/\lambda_L^2 = 4\pi n e^2/m^*$ and usually the large anisotropy of λ_L is attributed to a large mass enhancement [1,2]. A mass enhancement could follow from *e.g.* spin-charge separation [3,4,5]. Alternatively, elastic [6] or inelastic [7] Fermi-liquid corrections, as well as spin-charge separation, may cause a strongly incoherent charge transport along the c axis. No plasma pole is found in the normal state, whereas in the superconducting state in some of the materials a zero-crossing of the real part of the dielectric function (ϵ') is found at an energy two orders of magnitude below the value expected from LDA band structure calculations. In this paper we shall argue that the discrepancy results not from a strong mass-enhancement, but from a strong quasi-particle damping for $\vec{E}/c$, both in the normal and in the superconducting state.

Single crystals of $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$ with nominal Sr contents of 10 and 15 % were grown by the traveling-solvent floating-zone method [8]. Electron probe micro analysis showed the correct phase with no contamination or inclusion of second phases, and a homogeneous distribution of strontium. The crystals have sharp superconducting transitions (35 K at optimal doping, with 90 % of the transition within 3 K as determined from AC susceptibility measurements at 3 Gauss, 90 Hz).

Neutron diffraction measurements demonstrated that the as-grown boules contain large single crystalline grains. Samples for reflectivity measurements were cut perpendicular to the b axis and were mechanically polished to optical quality. The surface in the ac plane was approximately $4 \times 7 \text{ mm}^2$. X-ray Laue backscattering showed a correct orientation with sharp, well-defined single diffraction spots.

Polarized infrared reflectivity spectra were measured in two different laboratories between 10 and 10000 cm^{-1} at temperatures between 10 and 300 K using rapid-scan Fourier-transform spectrometers equipped with a continuous-flow cryostat. The data obtained in the two laboratories on nominally identical crystals are in a good agreement with each other, and with those of Tamasaku *et al.* [1].

In the inset of Fig. 1 we display the reflectivity of a $\text{La}_{1.85}\text{Sr}_{0.15}\text{CuO}_4$ single crystal with $\vec{E}/c$ in the normal state at 33 K. The spectrum is typical for an ionic insulator. At low frequencies there is a Hagen-Rubens type of upturn, $R(\nu) = 1 - 2(\sigma_0/\nu)^{1/2}$, characteristic of a poor conductor, where $\text{Re}\sigma(\nu)$ is dominated by

$\sigma_0(1 + \nu^2/\gamma^2)^{-1}$, with $\sigma_0 \approx 7 \text{ } \Omega^{-1}\text{cm}^{-1}$. A closer inspection, using a Drude-Lorentz model with a Drude oscillator and 4 phonons (see Fig. 1 caption), indicates a featureless and almost constant value of the electronic part of $\sigma(\nu)$: A good fit in the range of 20 to 650 cm^{-1} can only be obtained (see Fig. 1 inset) if γ is taken to be larger than 0.5 eV. With these parameters a zero-crossing of $\epsilon' = \tilde{\epsilon}_\infty - 2\sigma_0\gamma(\nu^2 + \gamma^2)^{-1}$ occurs for $\nu^2 < 0$, and hence the plasmon has a diffusive pole in the normal state. By integrating the corresponding expression for $\text{Re}\sigma(\nu)$, we can put a lower bound on ν_p of $\sqrt{2}\sigma_0\gamma = 0.15 \text{ eV}$. Interestingly this is much closer to estimates of the c -axis plasma frequency based on the single-electron effective mass in this solid. From such an RPA-LDA analysis for the La_2CuO_4 system one obtains a screened ab -plane plasma frequency of 2 eV, well above the onset of the interband electron-hole continuum at 0.5 eV, and a screened c -axis plasma frequency at 0.35 eV, *i.e.*, below the interband electron-hole continuum [9]. It is interesting to notice that experimentally the situation *vis à vis* Landau damping is reversed: In the ab -plane dielectric function a clear, though strongly damped, plasma pole is observed near 1 eV [10], whereas a plasmon is absent in the c -axis dielectric function due to overdamping. Such loss of coherence is also born out by confinement of holons to the planes [11], due to the fact that an interlayer hopping process requires a spinon-holon combination as an intermediate state.

Let E_g^* be the *effective* value of the gap, or gap-distribution. We will assume $E_g^* = 3.5k_B T_c$, which becomes exact in the limit of a weak coupling s -wave superconductor. In the superconducting state we should make a distinction between the high- and low-frequency parts of the spectrum, far above and below E_g^* ($\approx 80 \text{ cm}^{-1}$ for $\text{La}_{1.85}\text{Sr}_{0.15}\text{CuO}_4$). The former remains relatively unaffected by the transition, whereas for the latter range of frequencies we expect to find temperature dependence in both the real and imaginary parts of the electronic contribution to the conductivity. For example, for an isotropic s -wave BCS superconductor one expects a decrease of $\sigma(\nu)$ for $\nu \approx E_g^*/2$ as indicated in Fig. 2. In addition there may be a strong decrease of γ for $T < T_c$ as has been reported for the in-plane infrared [12,13] and microwave [14] response of high- T_c superconductors, and the c -axis infrared response of $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ [1].

We analyze our data in the superconducting state using the two-fluid Gorter-Casimir model at frequencies up to 100 cm^{-1} , *i.e.*, with the model dielectric function [15]

$$\epsilon = \tilde{\epsilon}_\infty - \frac{\nu_\phi^2}{\nu^2} + i \frac{2\sigma_0}{\nu(1 - i\nu/\gamma)}.$$

The dashed curve in Fig. 1 corresponds to the fit-parameters used by Tamasaku *et al.* for 8 K [1]. Note that with their set of parameters in the superconducting state nearly all oscillator strength under σ collapses

into the δ -function at the origin. This essentially corresponds to the clean limit. A much better fit is obtained if the spectra are modeled with a broad and featureless electronic component of σ , similar to the normal state. Initially we varied all parameters. At all temperatures the best fits indicate that $\nu/\gamma \ll 1$, and only small and unsystematic changes of $\tilde{\epsilon}_\infty$ with temperature are obtained. Therefore we repeated the analysis with $\gamma \rightarrow \infty$, and replacing $\tilde{\epsilon}_\infty$ by the sum of ϵ_∞ and the oscillator strengths of Fig. 1. To estimate the influence of dispersion of the optical phonons, we also did this analysis using the full set of phonon parameters of Fig. 1. The temperature dependence of the remaining two parameters ($(\nu_\phi(T)/\nu_\phi(0))^2$ and $\sigma_0(T)/\sigma_0(T_c)$), with $\nu_\phi(0) = 180 \text{ cm}^{-1}$ and $\sigma_0(31 \text{ K}) = 6.7 \text{ } \Omega^{-1}\text{cm}^{-1}$ are displayed in Fig. 2, and the reflectivity data together with the fitted curves are shown for three different temperatures in Fig. 1.

Also shown in Fig. 2 are the results of model calculations for the dirty limit of isotropic s -wave [16] and d -wave [17] superconductors, assuming standard ratios of E_g^*/T_c for these two models, and assuming a temperature-independent scattering rate. The conductivity was calculated for $\nu = 50 \text{ cm}^{-1}$. This frequency is close both to BCS ratio $3.5k_B T_c = 80 \text{ cm}^{-1}$ and to the gap value deduced from neutron scattering [18]. As a result we observe a steep drop of σ for $T < T_c$, and the change of analytical behavior at the temperature where $E_g(T) = h\nu$. For d -wave pairing the calculated temperature dependence of σ is smooth, and quite close to the experimentally determined values. If we would assume that in addition there is a drop of the decay rate when the gap opens, the theoretical curves would have an even steeper temperature dependence below T_c . For this reason we attribute the decrease of σ for $T < T_c$ exclusively to the opening of a gap, *i.e.*, *without* assuming a change of the electronic decay rate. For $\sigma_0(T)$ a reasonable agreement exists with the d -wave model, whereas there is no good agreement with the s -wave model. For $f_s(T) = (\nu_\phi(T)/\nu_\phi(0))^2$ the situation is reversed: f_s follows roughly a $1 - (T/T_c)^4$ law, which differs strongly from the d -wave pairing model, and lies somewhat above the s -wave pairing curve. For $\sigma_0(T)$ the comparison with the s -wave model is slightly improved if we postulate the existence of constant background (possibly spurious) conductivity in our samples. Interestingly, the jump in $\chi^c(T)/\chi^{ab}(T)$, as recently reported by Shibauchi *et al.* [2], is very well reproduced within this picture, as well as the difference between λ_{ab} and λ_c , if we assume a clean limit picture for the ab -plane response.

From a direct inspection of $\sigma(\nu)$ obtained from Kramers-Kronig analysis (Fig. 1 lower panel) we find no signature of a gap in the data [19], possibly due to limitations in signal-to-noise ratio and the presence of a tail of the optical phonon at 240 cm^{-1} . As is clear from the calculated conductivity (the dashed curve) based on

Mattis-Bardeen theory, even in the case of an isotropic s -wave superconductor a gap would be hard to distinguish. In the present case the difficulty arises from the low value of σ due to a strong damping. We notice that the situation is reversed compared to the planar response. In the latter case E_g^* is situated in the Lorentzian tail of a narrow Drude peak, which, due to the low value of σ , makes a gap difficult to observe [20].

In Fig. 3 we classify various regimes that can occur depending on the relevant energy scales: First there is the pair-breaking energy scale E_g^* . Second is the screened plasma frequency $\tilde{\nu}_p = \tilde{\epsilon}_\infty^{-1/2}\nu_p$, (the screening may include optical phonons depending on how far down the plasmon is pushed due to screening and damping effects). Similar parameters were also used by Uemura *et al.* [22] to classify clean-limit superconductors corresponding to their Fermi energy ($\propto h\nu_p$ for a 2D Fermi liquid). We extend this classification with the scattering rate γ (using $2\gamma\sigma_0 = \nu_p^2$). We scale both E_g^* and γ to $\tilde{\nu}_p$.

The region labeled ‘CL’ corresponds to the clean limit where $\gamma \ll E_g^*$, and this region contains the ‘exotic’ superconductors considered by Uemura *et al.* [22], in particular the high- T_c cuprate superconductors characterized by their in-plane electrodynamical properties. Most classical superconductors fall in the region labeled ‘MB’, where the infrared properties can be described in the context of dirty-limit Mattis-Bardeen theory. In the CL and MB regions a plasmon is found well above E_g^* in the normal as well as in the superconducting state.

In the regions labeled ‘OP’ and ‘RP’, the plasmon is overdamped in the normal state, as with $\gamma > \tilde{\nu}_p$ a zero crossing of ϵ' no longer exists. In the superconducting state the ‘missing area’ of the conductivity due to the opening of the gap is transferred to the δ -function at $\nu = 0$, so that ϵ' crosses zero at $\tilde{\nu}_p\sqrt{\pi E_g^*/2h\gamma}$. Unless this frequency is below the gap, the plasma mode will be damped (OP region). Hence the requirement for the existence of a long-lived collective mode is, that $E_g^*/\tilde{\nu}_p > \pi\tilde{\nu}_p/2\gamma$. This ‘phason’ mode has been described by Doniach and Inui [23] assuming Josephson coupling between the layers. Using Anderson’s expressions [24] for collective modes in the superconducting state we have recently shown [25], that the plasmon gradually changes from a collective oscillation of quasi-particles for $\nu \gg E_g^*$, to an oscillating current carried by the condensate for $\nu \ll E_g^*$. This region is labeled ‘RP’ (re-entrant phason). Our investigation indicates that the c -axis response of $\text{La}_{1.85}\text{Sr}_{0.15}\text{CuO}_4$ lies in the RP region. Although the c -axis response data for other high- T_c materials are very limited, the far infrared results of Noh *et al.* [26] and of Tajima *et al.* [27] indicate that also the c -axis response of $\text{Nd}_{1.85}\text{Ce}_{0.15}\text{CuO}_{4-y}$ and of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ should be placed in the RP region. In both these materials the c -axis plasmon, attributed to a sphere resonance by Noh *et al.* [26], is found at very low energy of approximately 10

cm^{-1} , and in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ a very strong damping of c -axis electronic response [27] is observed.

The two regions labeled CLP ('clean local pair') and OLP ('overdamped local pair') correspond to clean and dirty limit superconductors with a pair-breaking energy larger than the plasma frequency. In such systems the phase transition is induced by thermal activation of phasons, while the pairs remain intact up to a higher de-pairing temperature scale. This corresponds to Bose-Einstein condensation of local pairs. According to the analysis of Tamasaku *et al.* [1] the c -axis phason of $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ would be located in the CLP region.

We conclude that the absence of a c -axis plasmon in the normal state of high- T_c cuprate superconductors results from an anomalously strong damping of the transport perpendicular to the CuO_2 planes. This assignment also alleviates the discrepancy by two orders of magnitude existing in the literature between the plasma frequency obtained from optical experiments and that from the single-electron interlayer-hopping matrix element. The appearance of a c -axis phason mode, as observed in the superconducting state, is a direct consequence of the anomalously strong damping of the charge-carrier transport perpendicular to the planes. The decrease in σ for $T < T_c$ can be fully accounted for by the opening of a gap, the presence of which is a necessary consequence of the f -sum rule. There is no indication for a sudden decrease of the optical decay rate for $\vec{E}/\vec{c}$ when $T < T_c$.

Acknowledgements We gratefully acknowledge stimulating discussions with M. J. Rice, and useful comments by T. M. Rice and P. W. Anderson during the preparation of this manuscript. This investigation was supported by the Netherlands Foundation for Fundamental Research on Matter (FOM) with financial aid from the Nederlandse Organisatie voor Wetenschappelijk Onderzoek (NWO).

- [14] D. A. Bonn *et al.*, Phys. Rev. B **47**, 11314 (1993).
- [15] D. van der Marel *et al.*, Phys. Rev. B **43**, 8606 (1991).
- [16] D. C. Mattis and J. Bardeen, Phys. Rev. **117**, 912 (1958).
- [17] H. Won and K. Maki, Phys. Rev. B **49**, 1397 (1994).
- [18] T.E. Mason, G. Aeppli, and H.A. Mook, Phys. Rev. Lett. **68**, 1414 (1993).
- [19] The small bump $\propto -\text{Im}\epsilon^{-1} \times 13.0\Omega^{-1}\text{cm}^{-1}$ can be attributed within an effective medium approach to spurious absorption at enclosures with a non-nominal composition. A. M. Gerrits *et al.*, preprint.
- [20] K. Kamarás *et al.*, Phys. Rev. Lett. **64**, 84 (1990).
- [21] J. H. Kim *et al.*, to be published.
- [22] Y. J. Uemura *et al.*, Phys. Rev. Lett. **66**, 2665 (1991).
- [23] S. Doniach and M. Inui, Phys. Rev. B **41**, 6668 (1990).
- [24] P. W. Anderson, Phys. Rev. **112**, 1900 (1958).
- [25] D. van der Marel, to be published.
- [26] T. W. Noh, S. G. Kaplan, and A. J. Sievers, Phys. Rev. B **41**, 307 (1990).
- [27] S. Tajima *et al.*, Phys. Rev. B **48**, 16164 (1993).

FIG. 1. Upper panel: Reflectivity of $\text{La}_{1.85}\text{Sr}_{0.15}\text{CuO}_4$ at 10 (squares), 20 (circles), and 27 K (triangles) with least-square fitted curves. Dashed curve: fit-parameters for 8 K taken from Tamasaku *et al.* [1]. Inset: Reflectivity at 33 K (triangles) with Drude-Lorentz fit. The parameters are $\epsilon_\infty = 4.75$, $\sigma_0 = 7 \Omega^{-1}\text{cm}^{-1}$, $\gamma > 4600 \text{ cm}^{-1}$, so that $\nu_p > 1200 \text{ cm}^{-1}$. The TO phonons were parametrized with $\{\omega_i (\text{cm}^{-1}), \gamma_i (\text{cm}^{-1}), S_i\}$ ($i = 1 \dots 4$): $\{241.5, 24.8, 17.6\}$, $\{312.0, 3.0, 0.019\}$, $\{351.0, 3.0, 0.044\}$, $\{494.1, 12.8, 0.33\}$. Lower panel: Optical conductivity obtained from Kramers-Kronig analysis at 10, 20, and 27 K (solid symbols, from bottom to top). Chained curve: $-\text{Im}\epsilon^{-1} \times 13.0\Omega^{-1}\text{cm}^{-1}$. Open symbols: conductivities with the chained curves subtracted. Dashed curve: calculation based on the Mattis-Bardeen model, taking into account the phonon contribution.

FIG. 2. Temperature dependence of σ_0 (solid symbols) and ν_ϕ^2 (open symbols) corresponding to the fits in Fig. 1. Squares: sample 1. Circles and triangles: sample 2. Open and closed squares and open circles: with a constant $\tilde{\epsilon}_\infty$. Open and closed triangles: with full frequency dependence of phonon oscillators in $\tilde{\epsilon}_\infty$. Solid circles: conductivities at 50 cm^{-1} , after subtracting the loss function peaks as indicated in the lower panel of Fig. 1. Dashed curve: $1 - (T/T_c)^4$. Chained and solid curves: simulation for s - and d -wave pairing, respectively. Dotted curve: s -wave pairing plus constant background conductivity. The simulations of σ_s/σ_n are at $\nu = 50 \text{ cm}^{-1}$.

FIG. 3. Phase diagram in the $(\gamma/\tilde{\nu}_p)-(E_g^*/h\tilde{\nu}_p)$ plane [21].

-
- [1] K. Tamasaku, Y. Nakamura, and S. Uchida, Phys. Rev. Lett. **69**, 1455 (1992).
 - [2] T. Shibauchi *et al.*, Phys. Rev. Lett. **72**, 2263 (1994).
 - [3] P. W. Anderson, Science **235**, 1196 (1987).
 - [4] F. C. Zhang and T. M. Rice, Phys. Rev. B **37**, 3759 (1988).
 - [5] M. J. Rice and Y. R. Wang, Phys. Rev. B **48**, 12921 (1993).
 - [6] M. J. Graf, D. Rainer and J. A. Sauls, Phys. Rev. B **47**, 12098 (1993).
 - [7] A. G. Rojo and K. Levin, Phys. Rev. B **48**, 16861 (1993).
 - [8] V. H. M. Duijn, *et al.*, to be published.
 - [9] M. Czyzyk, and D. van der Marel, to be published.
 - [10] J. H. Kim *et al.*, Physica C **185-189**, 1019 (1991).
 - [11] P. W. Anderson, Science **256**, 1526 (1992).
 - [12] D. B. Romero *et al.*, Phys. Rev. Lett. **68**, 1590 (1992).
 - [13] M. Nuss *et al.*, Phys. Rev. Lett. **66**, 3305 (1991).